

负极铝箔 (Etched Alum Cathode Foil)

规格	材料 纯度	厚度	容量	抗拉		抗弯	Cl ⁻ 含量	Cu ²⁺ 含量	可裁宽
		Thickness	Capacitance						
Specification	Foil Purity	um	uf/cm ²	Tensile Strength		Bending Strength	Cl ⁻ Residual	Cu ²⁺ Residual	Cutting Width
	%	±2	(+30% , -10%)	N/cm	kgf/cm	counts/cm	mg/m ²	mg/m ²	mm
ECM-2021	≥98.4	22	100	15.6	1.6	65	≤1.0	≤5.0	≥6.0
ECM-3011	≥98.4	28	150	18.6	1.9	70	≤1.0	≤5.0	≥5.0
ECM-3021			200	17.6	1.8	70	≤1.0	≤5.0	≥6.0
ECM-4011	≥98.4	38	350	18.6	1.9	80	≤1.0	≤5.0	≥5.0
ECM-4021			400	18.6	1.9	80	≤1.0	≤5.0	≥5.0
ECM-4031			450	18.6	1.9	80	≤1.0	≤5.0	≥5.0
ECM-5011	≥98.4	42	350	21.5	2.2	90	≤1.0	≤5.0	≥3.5
ECM-5031			500	19.5	2.0	90	≤1.0	≤5.0	≥5.0
ECM-5013	≥98.4	48	350	22.5	2.3	100	≤1.0	≤5.0	≥2.2
ECM-5023			450	22.5	2.3	100	≤1.0	≤5.0	≥2.2
ECM-5033			500	22.5	2.3	100	≤1.0	≤5.0	≥2.2
ECM-5043			600	18.6	1.9	90	≤1.0	≤5.0	≥5.0
ECL-5021	≥99.4	46	450	18.6	1.9	90	≤1.0	≤5.0	≥5.0